



Sintergewebe	Bezeichnung	Geometrische Porengrösse	Dicke	Porösität	Druckverlust	As	Rp	Gewicht	spez. Durchfluss-Kennzahl
		µm	mm	%	mbar	mm ² / cm	N / cm	kg / m ²	Eu
Topmesh 2-Lagig	TM2-KT 2	10	0.7	60	4.6	1.3	207	2.3	3481
	TM2-KT 5	14	0.7	60	3.8	1.3	207	2.3	2876
	TM2-KT 10	21	0.7	60	1.8	1.3	207	2.3	1362
	TM2-BM 15	15	0.7	60	0.71	1.3	207	2.3	537
	TM2-BM 20	20	0.7	60	0.53	1.3	207	2.3	401
	TM2-BM 25	25	0.7	60	0.48	1.3	207	2.3	363
	TM2-BM 30	30	0.7	60	0.4	1.3	207	2.3	303
	TM2-BM 40	40	0.7	60	0.38	1.3	207	2.3	288
	TM2-QM 50	50	0.7	60	0.1	1.3	207	2.3	76
	TM2-QM 60	61	0.7	60	0.09	1.3	207	2.3	68
	TM2-QM 80	80	0.7	60	0.06	1.3	207	2.3	45
	TM2-QM 100	100	0.8	70	0.04	1.3	207	1.77	30
	TM2-QM 150	150	0.8	70	0.03	1.3	207	1.77	23
	TM2-QM 200	250	1.4	65	0.03	1.3	207	3.75	23
	TM2-QM 500	530	1.4	65	0.02	1.3	207	3.75	15

Version: 01.05.2015